



#### **TM127S BU**

# DuPont™ ProShield® 6 SFR

DuPont™ ProShield® 6 SFR Coverall. Standard Fit Hood. Elastic Wrists and Ankles. Serged Seams. Blue.

Name Description

**Full Part Number** TM127SBUxx0025yy (xx=size;yy=option code)

Fabric/Materials ProShield® 6 SFR

Design Coverall w/ Hood, Elastic Wrists and Ankles

Seam Serged

Color Blue

Quantity/Box 25 per box

**Option Codes** 00,PI

#### **FEATURES & PRODUCT DETAILS**

ProShield® 6 SFR is a Lightweight, disposable overgarment designed to help protect and preserve primary flame-resistant garments. It provides a barrier against non-hazardous particles and aerosols while not contributing to burn injury. ProShield® 6 SFR garments won't ignite and continue to burn when exposed to a flame source. They are flame retardant treated, not inherently flame resistant, and are intended to be worn over your primary flame resistant garments.


- Stormflaps.
- Attached hood with elastic around face opening
- Elastic opening for tighter fit at wrist
- Elastic opening for tighter fit at ankle

## **AVAILABLE OPTIONS**

| Option<br>Code | Description | Sizes                         | Part Number      |
|----------------|-------------|-------------------------------|------------------|
| 00             | Standard    | SM,MD,LG,XL,2X,3X,4X,5X,6X,7X | TM127SBUxx002500 |
| PI             | Standard_PI | MD,LG,XL,2X,3X,4X             | TM127SBUxx0025PI |

#### **SPECIFICATIONS**

- The garment shall be blue in color.
- The garment shall be a hooded coverall design.
- The garment shall be constructed of DuPont™ ProShield® 6 SFR -- a nonwoven wood-pulp/polyester fabric that is treated to provide flame retardancy and liquid repellancy characteristics.
- The garment shall have elastic ankles.
- The garment shall have a front zipper closure.
- The garment shall have elastic wrists.
- The garment shall have serged seams.
- The garment shall have a standard hood with elastic around the face.



## FINISHED DIMENSIONS

| Size | Sleeve Length | Chest Width | Inseam | Fits Chest      | Fits Height  |
|------|---------------|-------------|--------|-----------------|--------------|
| SM   | 33 3/4        | 24 1/4      | 28     | 35 1/4 - 38 3/4 | 5'0" - 5'7"  |
| MD   | 33 3/4        | 24 1/4      | 28     | 35 1/4 - 38 3/4 | 5'3" - 5'7"  |
| LG   | 35            | 25 3/4      | 29     | 38 1/4 - 41 3/4 | 5'5" - 5'9"  |
| XL   | 36 1/2        | 27 1/4      | 29 1/2 | 41 1/4 - 44 3/4 | 5'8" - 6'2"  |
| 2X   | 38 1/4        | 28 3/4      | 30 1/2 | 44 1/4 - 47 3/4 | 6'0" - 6'4"  |
| 3X   | 38 1/2        | 30 1/4      | 31 1/2 | 47 1/4 - 50 3/4 | 6'2" - 6'4"  |
| 4X   | 39 1/2        | 32          | 32 1/2 | 50 3/4 - 54 1/4 | 6'4" - 6'7"  |
| 5X   | 40 1/2        | 33 1/2      | 33 1/2 | 53 3/4 - 57 1/4 | 6'7" - 6'10" |
| 6X   |               |             |        |                 | 6'9" - 7'1"  |
| 7X   |               |             |        |                 | 7'0" - 7'4"  |

### ADDITIONAL EQUIPMENT NEEDED

- Tempro® garments are flame retardant treated, not inherently flame resistant, and are intended to be worn over primary flame-resistant garments. Tempro® garments will not provide thermal / fire protection if worn alone.
- Wear other appropriate PPE such as, but not limited to, respiratory, eye, head, hand, and foot protection based on the hazard assessment.

#### **Physical Properties**



Data relating to mechanical performance of the fabrics used in DuPont chemical protective clothing, listed for the selected garment according to the test methods and relevant European standard, if applicable. Such properties, including abrasion and flex-cracking resistance, tensile strength and puncture resistance can help in the assessment of protective performance.

| Property                              | Test Method | Typical Result         |
|---------------------------------------|-------------|------------------------|
| Basis Weight                          | ASTM D3776  | 2.4 oz/yd <sup>2</sup> |
| Breaking Strength - Grab (CD)         | ASTM D5034  | 21 lb <sub>f</sub>     |
| Breaking Strength - Grab (MD)         | ASTM D5034  | 27 lb <sub>f</sub>     |
| Surface Resistivity (25°C / 55% RH)   | ASTM D257   | 4.0 x 10^7 ohms/square |
| Tear Resistance - Trap Tear (CD)      | ASTM D1117  | 10 lb <sub>f</sub>     |
| Tear Resistance - Trap Tear (MD)      | ASTM D1117  | 7 lb <sub>f</sub>      |
| Vertical Flame Resistance of Textiles | ASTM D6413  | < 2 seconds Afterflame |
| Vertical Flame Resistance of Textiles | ASTM D6413  | < 6 inches Char Damage |

<sup>1</sup> According to EN 14325 2 According to EN 14126 3 According to EN 1073-2 4 According to EN 14116 12

According to EN 11612 5 Front Tyvek ® / Back 6 Based on test according to ASTM D-572 7 See Instructions for Use for further information, limitations and warnings > Larger than < Smaller than <= Smaller than or equal to N/A Not Applicable STD DEV Standard Deviation

#### WARNING

\*CAUTION: This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is the user's responsibility to determine the level of toxicity and the proper personal protective equipment needed. The information set forth herein reflects laboratory performance of fabrics, not complete garments, under controlled conditions. It is intended for informational use by persons having technical skill for evaluation under their specific end-use conditions, at their own discretion and risk. Anyone intending to use this information should first verify that the garment selected is suitable for the intended use. In many cases, seams and closures have shorter breakthrough times and higher permeation rates than the fabric. Please contact DuPont for specific data. If fabric becomes torn, abraded or punctured, or if seams or closures fail, or if attached gloves, visors, etc. are damaged, end user should discontinue use of garment to avoid potential exposure to chemical. Since conditions of use are outside our control, we make no warranties, express or implied, including, without limitation, no warranties of merchantability or fitness for a particular use and assume no liability in connection with any use of this information. This information is not intended as a license to operate under or a recommendation to infringe any patent or technical information of DuPont or others covering any material or its use.

Cellosolve® and Selexol™ are registered trademarks of Dow Chemicals Company. Skydrol® is a registered trademark of Solutia.

- \*Liquid barrier performance varies based on the amount of liquid that may get on the garment, the length of time the liquid is on the garment, applied pressure and certain physical properties of the liquid. Tyvek®400, Tyvek® 400 D, ProShield®, ProShield® 10, ProShield® 60, Tyvek® 400 FC, and ProShield® 70 garments are not appropriate if during use they are getting wet (liquid is dripping or running, or it is wet to the touch) or if spotting is observed on skin or garments worn under the protective garment. Tyvek® 500 and Tyvek® 600 offer improved liquid barrier, but may not be appropriate if spotting is observed on the skin or garments worn under the protective garment. In applications where a higher liquid barrier is needed, consider Tychem® 2000 and Tychem® 4000 garments with taped seams.
- \*Serged and bound seams are degraded by some hazardous liquid chemicals, such as strong acids, and should not be worn
  when these chemicals are present.