



Model TY500S WH

# Tyvek® 400

DuPont™ Tyvek® 400, model TY500S WH. Sleeve. Stitched internal seam. Elastic openings. White.

| Name             | Description              |
|------------------|--------------------------|
| Full Part Number | TYVPS30SWHA0             |
| Fabric/Materials | Tyvek® 400               |
| Design           | Sleeve with elastics     |
| Seam             | Stitched (internal)      |
| Color            | White                    |
| Quantity/Box     | 200 per box, bulk packed |

## FEATURES & PRODUCT DETAILS

DuPont™ Tyvek® 400, model TY500S WH. 46cm long sleeve available in white and in one size. Stitched internal seams. Adjustable arm opening.

Specially designed for use with Tyvek® apparel, Tyvek® accessories can help offer enhanced protection for body parts that are more exposed to hazardous substances.

Tyvek® garments and accessories are composed of flash spun high density polyethylene, providing an ideal balance of protection, durability and comfort. Tyvek® is permeable to both air and water vapour, yet repels water-based liquids and aerosols. It offers an excellent barrier against fine particles and fibres (down to 1 micron in size), is ultra-low-linting and antistatically treated. Silicon non-added.

Applications for Tyvek® 400 accessories include pharmaceutical handling, chemical protection, lead and asbestos abatement /remediation, general maintenance/operations, spray painting and general clean-up, amongst many others.

- Available in one size (46cm long)
- Antistatic treatment (EN 1149-1) - on inside; see footnotes

#### **ADDITIONAL EQUIPMENT NEEDED**

- This garment only provides partial body coverage. It may be worn in combination with other chemical resistant PPE as required based on the hazard assessment.
- This garment only provides partial body coverage. It may be worn in combination with other chemical resistant PPE as required based on the hazard assessment.
- Wear other appropriate PPE such as, but not limited to, respiratory, eye, head, hand, and foot protection based on the hazard assessment.

## Physical Properties



Data relating to mechanical performance of the fabrics used in DuPont chemical protective clothing, listed for the selected garment according to the test methods and relevant European standard, if applicable. Such properties, including abrasion and flex-cracking resistance, tensile strength and puncture resistance can help in the assessment of protective performance.

| Property                                           | Test Method          | Typical Result                     | EN                  |
|----------------------------------------------------|----------------------|------------------------------------|---------------------|
| Abrasion Resistance <sup>7</sup>                   | EN 530 Method 2      | >100 cycles                        | 2 of 6 <sup>1</sup> |
| Basis Weight                                       | DIN EN ISO 536       | 41.5 g/m <sup>2</sup>              | N/A                 |
| Colour.                                            | N/A (598)            | White                              | N/A                 |
| Exposure to high Temperature                       | N/A (598)            | Melting point 135 °C               | N/A                 |
| Exposure to low Temperature                        | N/A (598)            | Flexibility retained down to -73°C | N/A                 |
| Flex Cracking Resistance <sup>7</sup>              | EN ISO 7854 Method B | >100000 cycles                     | 6 of 6 <sup>1</sup> |
| Puncture Resistance                                | EN 863               | >5 N                               | 2 of 6 <sup>1</sup> |
| Surface Resistance at RH 25%, inside <sup>7</sup>  | EN 1149-1            | ≤ 2,5x10 <sup>9</sup> Ohm          | N/A                 |
| Surface Resistance at RH 25%, outside <sup>7</sup> | EN 1149-1            | ≤ 2,5x10 <sup>9</sup> Ohm          | N/A                 |
| Tensile Strength (MD)                              | DIN EN ISO 13934-1   | >30 N                              | 1 of 6 <sup>1</sup> |
| Tensile Strength (XD)                              | DIN EN ISO 13934-1   | >30 N                              | 1 of 6 <sup>1</sup> |
| Thickness (PPSH-249)                               | DIN EN ISO 534       | 140 µm                             | N/A                 |
| Trapezoidal Tear Resistance (MD)                   | EN ISO 9073-4        | >10 N                              | 1 of 6 <sup>1</sup> |
| Trapezoidal Tear Resistance (XD)                   | EN ISO 9073-4        | >10 N                              | 1 of 6 <sup>1</sup> |

1 According to EN 14325 2 According to EN 14126 3 According to EN 1073-2 4 According to EN 14116 12  
 According to EN 11612 5 Front Tyvek ® / Back 6 Based on test according to ASTM D-572 7 See Instructions for  
 Use for further information, limitations and warnings > Larger than < Smaller than N/A Not Applicable STD DEV  
 Standard Deviation

GARMENT PERFORMANCE



Information relating to the protective performance of a garment according to European standards where applicable. Includes important characteristics such as protection against radioactive contamination, seam strength and shelf life. Inward leakage and resistance to penetration by liquids, according to the relevant Type classification, are also detailed.

| Property              | Test Method | Typical Result | EN  |
|-----------------------|-------------|----------------|-----|
| Shelf Life (PPSH-190) | N/A (598)   | 5 years        | N/A |

1 According to EN 14325    3 According to EN 1073-2    12 According to EN 11612    13 According to EN 11611    5 Front Tyvek ® / Back    6 Based on test according to ASTM D-572    7 See Instructions for Use for further information, limitations and warnings    11 Based on the average of 10 suits, 3 activities, 3 probes    > Larger than    < Smaller than    N/A Not Applicable    \* Based on lowest single value

COMFORT



The comfort of a protective garment during use is largely determined by its weight, its permeability to vapour and air (breathability) and insulating properties. Data on these attributes is provided according to test method and, as with other data, can be compared by garment.

| Property                         | Test Method        | Typical Result   | EN  |
|----------------------------------|--------------------|------------------|-----|
| Air Permeability (Gurley method) | ISO 5636-5         | > 45 s           | N/A |
| Air Permeability (Gurley method) | ISO 5636-5         | Yes              | N/A |
| Thermal Resistance, Rct          | EN 31092/ISO 11092 | 16.3*10-3 m2*K/W | N/A |
| Thermal Resistance, clo value    | EN 31092/ISO 11092 | 0.105 clo        | N/A |
| Water Vapour Resistance, Ret     | EN 31092/ISO 11092 | 11.3 m2*Pa/W     | N/A |

2 According to EN 14126    5 Front Tyvek ® / Back    > Larger than    < Smaller than    N/A Not Applicable

PENETRATION AND REPELLENCY



A specific test method, EN ISO 6530, is used to measure the indexes of penetration, absorption and repellency of protective clothing material exposed to liquid chemicals. Results listed here reflect the penetration resistance and repellency of DuPont fabrics to 30% sulphuric acid and 10% sodium hydroxide.

| Property                                                     | Test Method | Typical Result | EN                  |
|--------------------------------------------------------------|-------------|----------------|---------------------|
| Repellency to Liquids, Sodium Hydroxide (10%)                | EN ISO 6530 | >95 %          | 3 of 3 <sup>1</sup> |
| Repellency to Liquids, Sulphuric Acid (30%)                  | EN ISO 6530 | >95 %          | 3 of 3 <sup>1</sup> |
| Resistance to Penetration by Liquids, Sodium Hydroxide (10%) | EN ISO 6530 | <1 %           | 3 of 3 <sup>1</sup> |
| Resistance to Penetration by Liquids, Sulphuric Acid (30%)   | EN ISO 6530 | <1 %           | 3 of 3 <sup>1</sup> |

1 According to EN 14325    > Larger than    < Smaller than



PARTICLE BARRIER



Particle barrier performance is measured by exposing a fabric to a particle challenge and then determining the penetration of particles by means of a counter. DuPont measure the particle barrier of its fabrics to Aloxite dust according to a proposed European test method and the Chrysotile asbestos fibres according to a Haskell laboratory test method.

| Property                        | Test Method | Typical Result                              | EN  |
|---------------------------------|-------------|---------------------------------------------|-----|
| Dry Linting Propensity, inside  | BS 6909     | 128 Average particle count/17 liters of air | N/A |
| Dry Linting Propensity, outside | BS 6909     | 56 Average particle count/17 liters of air  | N/A |

1 According to EN 14325    2 According to EN 14126    3 According to EN 1073-2    4 According to EN 14116    12  
According to EN 11612    5 Front Tyvek ® / Back    6 Based on test according to ASTM D-572    7 See Instructions for  
Use for further information, limitations and warnings    > Larger than    < Smaller than    N/A Not Applicable    STD DEV  
Standard Deviation

## WARNING

- The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.
- This garment and/or fabric are not flame resistant and should not be used around heat, open flame, sparks or in potentially flammable environments.
- Working in Ex-Zones: Please take this into account for your risk-assessment that the attached socks may isolate the wearer. There is the possibility that the garment and wearer cannot be grounded via the shoes and other measures for grounding the garment and the wearer are required